

ORAGUARD® Series 250AS Skid-Resistant PVC Laminating Film

Description

4.75-mil, matte transparent PVC film with a raised, skid-resistant, textured surface

Release Liner

55# silicone coated paper

Adhesive

Clear, solvent-based, permanent adhesive

Applications

A cold laminate for anti-skid protection of floor graphics. Meets the standards of ASTM D 2047 and BAM StVo §35 d3, (Federal Office for Material Testing: Automobile Safety Act).

Technical Data

Thickness (without liner and adhesive)	4.75 mil
Temperature Resistance	Adhered to aluminum, -40°F to +176°F, no variation
Fire Behavior (DIN 75200)	Adhered to steel, self-extinguishing
Fire Rating	ASTM E 84-07 Class "A"
Adhesive Power (FINAT TM-1, after 24 h, average)	Adhered to stainless steel: 2.74 lb/in
Tensile Strength (DIN EN ISO 527)	Along: Min. 19 MPa Across: Min. 19 MPa
Elongation at Break (DIN EN ISO 527)	Along: Min. 130% Across: Min. 150%
Seawaterability (DIN EN ISO 527)	Adhered to aluminum, after 100h/73°F, no variation
Shelf Life (68°F/50% relative humidity)	2 years
Minimum Life Expectancy (based on accepted application procedures on vertical surfaces)	3 months
Minimum Application Temperature	46°F
Available Lengths	150' (50-yard)
Available Widths (inches)	36, 40, 50, 54
Recommended to be used in combination with	ORAJET® Series 1663
System Skid Resistance (Federal Office for Material Testing: Automobile Safety Act)	Skid Distance Dry: <35" Skid Distance Wet: <55"

ORACAL® recommends that printed film be allowed to dry for at least 24 hours at 70°F (48-72 preferred) before applying a laminate.

Attention

Recycling Recommendation: Waste class similar to household waste, is to be recycled according to the local regulations.

Surfaces to which the material will be applied must be cleaned thoroughly of dust, grease or any contaminants. Freshly lacquered or painted surfaces should be allowed to stand for at least three weeks after complete curing. The compatibility of selected lacquers and paints should be tested by the end-user prior to use.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without any guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications, customers should independently determine the suitability of this material for their specific purpose, prior to use.

