

Description

Ultra flexible transparent Premium Cast PVC film with gloss surface and highest level of UV protection.

Release paper

Silicone coated paper, white, 90 g/m²

Adhesive

Solvent polyacrylate, permanent

Area of use

For the indoor and outdoor protection of large format digital prints.

Because of its very good conformability especially to rivets and corrugations ORAGUARD 293 is recommended for car wrapping in combination with ORAJET 3951.

Technical data

Thickness* (without protective film and adhesive)	30 micron
Dimensional stability (FINAT TM 14)	adhered to steel no shrinkage in cross direction, in length 0.1 mm max.
Temperature resistance	adhered to aluminium, -50°C to +110°C, no variation
Adhesive power* (FINAT TM 1, after 24h, stainless steel)	12 N/25 mm
Tensile strength (DIN EN ISO 527)	
along	min. 19 MPa
across	min. 19 MPa
Elongation at break (DIN EN ISO 527)	
along	min. 120%
across	min. 120%
Shelf life**	2 years
Application temperature	> +8°C
Service life by specialist application under vertical outdoor exposure (normal climate of Central Europe)	8 years

* average ** in original packaging, at 20°C and 50% relative humidity

Attention:

Due to the diversity of prints and printing techniques the user should test the suitability of the ORAGUARD laminating film for the specific print prior to use. Furthermore the application information published by ORAFOL is to be considered.

The statements in this information sheet are based upon our knowledge and practical experience. This data is intended only as a source of information and is given without guarantee and does not constitute a warranty. Due to the wide variety of possible uses and applications customers should independently determine the suitability of this material for their specific purpose, prior to use.