

## PRODUCT DATA SHEET



### Avery® Gloss Gold Film & Avery® Gloss Silver Film

issued: 18/09/2001

#### Introduction

Avery Gloss Gold/Silver Films are ideal for adding an element of glamour to glass windows and panels, mirrors and screens as well as to other transparent and opaque surfaces in interior and exterior design applications.

#### Description

Facefilm: 25 micron metallised polyester film  
Adhesive: permanent, acrylic based  
Backing paper: one side coated bleached kraft paper, 140 g/m<sup>2</sup>

#### Conversion

Avery Gloss Gold/Silver polyester films offer excellent cutting and weeding properties on a wide range of friction fed plotters as well as on flatbed plotters.

Avery Gloss Gold & Gloss Silver Films are not printable.

#### Features

- Excellent computerised signmaking characteristics.
- Bright silver and gold on both the top and adhesive side of the facefilm.
- Excellent adhesion to smooth surfaces.

#### Recommendations for use

- Interior signs and displays.
- Window graphics and retail signage.



[www.averygraphics.com](http://www.averygraphics.com)

Graphics Division  
Rijndijk 86, P.O. Box 118  
2394 ZG Hazerswoude – The Netherlands  
Tel +31 71 3421500 – Fax +31 71 3421538

## Physical properties

| Features                | Test method <sup>1</sup>     | Results            |
|-------------------------|------------------------------|--------------------|
| Caliper, facefilm       | ISO 534                      | 25 micron          |
| Dimensional stability   | DIN 30646                    | 0,1 mm. Max        |
| Adhesion, initial       | FINAT FTM-1, stainless steel | 320 N/m            |
| Adhesion, ultimate      | FINAT FTM-1, stainless steel | 520 N/m            |
| Flammability            |                              | Self extinguishing |
| Shelf life              | Stored at 22° C/50-55 % RH   | 2 years            |
| Durability <sup>2</sup> | Vertical exposure            |                    |
| Gold                    |                              | 2 years            |
| Silver                  |                              | 1 year             |

## Temperature range

| Features                | Results         |
|-------------------------|-----------------|
| Application temperature | Minimum: +10° C |
| Service temperature     | -40° to +150° C |

## Chemical resistance

| Features             | Test method <sup>1</sup>   | Results                      |
|----------------------|--|------------------------------|
| Humidity resistance  | 120 hours exposure   | No effect                    |
| Corrosion resistance | 120 hours exposure   | No contribution to corrosion |
| Water resistance     | 48 hours immersion   | No effect                    |
| Solvent resistance   | Applied to aluminium, exposed to oils, greases, aliphatic solvents, motor oils, heptane, kerosene and JP-4 fuel. | No effect                    |

### Important

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use. All technical data are subject to change.

### Warranty

Avery® branded materials are manufactured under careful quality control and are warranted to be free from defect in material and workmanship. Any material shown to our satisfaction to be defective at the time of sale will be replaced without charge. Our aggregate liability to the purchaser shall in no circumstances exceed the cost of the defective materials supplied. No salesman, representative or agent is authorised to give any guarantee, warranty, or make any representation contrary to the foregoing. All Avery® branded materials are sold subject to the above conditions, being part of our standard conditions of sale, a copy of which is available on request.

### 1) Test methods

More information about our test methods can be found on our website.

### 2) Durability

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.

