

TEST REPORT

No. : GZMR130914391

Date : Sep. 28, 2013

Page: 1 of 7

ZHANGJIAGANG FEITENG ALUMINIUM COMPOSITE PANEL CO. LTD
 HOUCHEG INDUSTRIY PARK, JINGANG TOWN, ZHANGJIAGANG CITY, JIANGSU 215631, CHINA

The following sample(s) was/ were submitted and identified on behalf of the client as:


Sample Name : ALUMINIUM COMPOSITE PANEL
 SGS Ref No. : GP130801506, SDHG1309007937FB
 Test Performed : Selected test(s) as requested by applicant
 Date of Receipt : Aug. 22, 2013
 Test Period : Aug. 22, 2013 to Sep. 28, 2013

Test result(s) : Please refer to the following page(s)

Test(s) Requested	Result(s)
EN 13501-1:2007+A1:2009	classification: C—s2, d0

*****To be continued*****

Signed for and on behalf of
 SGS-CSTC Standards Technical Services Co.,Ltd
 Guangzhou Branch



Kelly Lee
 Engineer

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To ensure the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

TEST REPORT

No. : GZMR130914391

Date : Sep. 28, 2013

Page: 2 of 7

Test Information:

Sample description: See photo

I. Test conducted

This test is conducted as per EN 13501-1:2007+A1:2009 Fire classification of construction products and building elements – Part 1: Classification using data from reaction to fire tests, Class C. And the test methods as following:

1. EN 13823:2010 Reaction to fire tests for building products - Building products excluding floorings exposed to the thermal attack by a single burning item.
2. EN ISO 11925-2:2010 Reaction to fire tests — Ignitability of building products subjected to direct impingement of flame — Part 2: Single-flame source test.

II. Details of classified product

Description

The details of the tested specimen given below have been prepared from information provided by the sponsor of the test. All values quoted are nominal, unless tolerances are given.

Color	White
Thickness	About 3 mm
Mass per unit area	About 4.36 kg/m ²

Mounting and fixing:

As per the client's requirement, the sample was fixed on the standard substrate by rivet.
 The specimen was tested free standing at a distance of at least 80 mm from the backing board.
 Both wings were clamped at the top and the bottom.

*****To be continued*****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client, and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) can be retained for 30 days only.

Attention: To ensure the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

TEST REPORT

No. : GZMR130914391

Date : Sep. 28, 2013

Page: 3 of 7

III. Test results

Test method	Parameter	Number of tests	Results
EN 13823	FIGRA (W/s)	3	239.5
	LFS < edge of specimen		Yes
	THR _{600s} (MJ)		11.6
	SMOGRA (m ² /s ²)		11.1
	TSP _{600s} (m ²)		84.0
	Flaming particles or droplets		No
EN ISO 11925-2 Exposure = 30 s	F _s ≤ 150 mm	6	Yes
	Ignition of the filter paper		No

Note: FIGRA — Fire growth rate index used for classification purposes [W/s]

LFS — Lateral flame spread [m]

THR_{600s} — Total heat release within 600 s [MJ]

SMOGRA — Smoke growth rate [m²/s²]

TSP_{600s} — Total smoke production within 600 s [m²]

IV. Classification and direct field of application

This classification has been carried out in accordance with EN 13501-1:2007+A1:2009.

Classification

The product, "ALUMINUM COMPOSITE PANEL", classification is as following,

Fire behaviour		Smoke production		Flaming droplets
C	—	s	2	, d 0

Reaction to fire classification: C—s2, d0

Note: 1. The classes with their corresponding fire performance are given in annex A.

2. Reaction to fire classification is based on the 7-step scale of A1 to F, where A1 is good and F is bad.

3. The above test was carried out by a SGS internal laboratory.

*****To be continued*****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To ensure the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

TEST REPORT

No. : GZMR130914391

Date : Sep. 28, 2013

Page: 4 of 7

Statement: The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

Warning:

This classification report does not represent type approval or certification of the product.

The test laboratory has, therefore, play no part in sampling the product for the test, although it holds appropriate references to the manufacturer's factory production control that is aimed to be relevant to the samples tested and that will provide for their traceability.

Annex A

Classes of reaction to fire performance for construction products excluding floorings and linear pipe thermal insulation products

Class	Test method(s)	Classification criteria	Additional classification
A1	EN ISO 1182 ^a and	$\Delta T \leq 30^\circ\text{C}$, and $\Delta m \leq 50\%$, and $t_f = 0$ (i.e. no sustained flaming)	-
	EN ISO 1716	$\text{PCS} \leq 2.0\text{MJ/kg}^a$ and $\text{PCS} \leq 2.0\text{MJ/kg}^{bc}$ and $\text{PCS} \leq 1.4\text{MJ/m}^2^d$ and $\text{PCS} \leq 2.0\text{MJ/kg}^e$	-
A2	EN ISO 1182 ^a or	$\Delta T \leq 50^\circ\text{C}$, and $\Delta m \leq 50\%$, and $t_f \leq 20\text{ s}$	-
	EN ISO 1716	$\text{PCS} \leq 3.0\text{MJ/kg}^a$ and $\text{PCS} \leq 4.0\text{MJ/m}^2^b$ and $\text{PCS} \leq 4.0\text{MJ/m}^2^d$ and $\text{PCS} \leq 3.0\text{MJ/kg}^e$	-
	EN 13823	$\text{FIGRA} \leq 120\text{W/s}$ and $\text{LFS} < \text{edge of specimen}$ and $\text{THR}_{600\text{s}} \leq 7.5\text{MJ}$	Smoke production ^f and Flaming droplets/particles ^g

*****To be continued*****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To ensure the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

TEST REPORT

No. : GZMR130914391

Date : Sep. 28, 2013

Page: 5 of 7

Class	Test method(s)	Classification criteria	Additional classification
B	EN 13823 and	FIGRA \leq 120W/s and LFS < edge of specimen and THR _{600s} \leq 7.5MJ	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ Exposure =30s	Fs \leq 150mm within 60 s	
C	EN 13823 and	FIGRA \leq 250W/s and LFS < edge of specimen and THR _{600s} \leq 15MJ	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ Exposure=30s	Fs \leq 150mm within 60 s	
D	EN 13823 and	FIGRA \leq 750W/s	Smoke production ^f and Flaming droplets/particles ^g
	EN ISO 11925-2 ⁱ Exposure=30s	Fs \leq 150mm within 60 s	
E	EN ISO 11925-2 ⁱ Exposure =15s	Fs \leq 150mm within 20 s	flaming droplets/particles ^h
F	No performance determined		

***** To be continued *****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To ensure the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

- ^a For homogeneous products and substantial components of non-homogeneous products.
- ^b For any external non-substantial component of non-homogeneous products.
- ^c Alternatively, any external non-substantial component having a PCS $\leq 2,0 \text{ MJ/m}^2$, provided that the product satisfies the following criteria of EN 13823: FIGRA $\leq 20 \text{ W/s}$, and LFS < edge of specimen, and THR_{600s} $\leq 4,0 \text{ MJ}$, and s1, and d0.
- ^d For any internal non-substantial component of non-homogeneous products.
- ^e For the product as a whole.
- ^f In the last phase of the development of the test procedure, modifications of the smoke measurement system have been introduced, the effect of which needs further investigation. This may result in a modification of the limit values and/or parameters for the evaluation of the smoke production.
s1 = SMOGRA $\leq 30 \text{ m}^2/\text{s}^2$ and TSP_{600s} $\leq 50 \text{ m}^2$; s2 = SMOGRA $\leq 180 \text{ m}^2/\text{s}^2$ and TSP_{600s} $\leq 200 \text{ m}^2$; s3 = not s1 or s2
- ^g d0 = No flaming droplets/ particles in EN 13823 within 600 s;
d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s;
d2 = not d0 or d1.
Ignition of the paper in EN ISO 11925-2 results in a d2 classification.
- ^h Pass = no ignition of the paper (no classification);
Fail = ignition of the paper (d2 classification).
- ⁱ Under conditions of surface flame attack and, if appropriate to the end-use application of the product, edge flame attack.

*****To be continued*****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client, and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To ensure the authenticity of testing /inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com

TEST REPORT

No. : GZMR130914391

Date : Sep. 28, 2013

Page: 7 of 7

Photo:



*****End of report*****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Terms-e-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Attention: To ensure the authenticity of testing / inspection report & certificate, please contact us at telephone: (86-755)83071443, or email: CN.Doccheck@sgs.com