

# Profit PVC Foam Board

## Technical Data Sheet



### PVC FOAM COLOUR WHITE

Thickness mm	1220×2440 mm	1560×3050 mm	2050×3050 mm
3	•	•	•
5	•	•	•

### PHYSICAL PROPERTIES OF PVC FOAM

Test	Test Method	Units	Average Result
Specific Gravity	In-House	g/cm <sup>3</sup>	0.50–0.70
Determination of Water Absorbtion	ISO 6 2:Method 1	%	0.19
Tensile Strength at Yield	ISO R527	MPa	19.37
Elongation at Break	ISO R527	%	17.89
Flexural Modulus	ISO 176	GPa	0.903
Charpy Impact Strength	ISO 179	kJm-2	1.43
Shore D Hardness	ISO 868	for 1–6 mm Value for 8–10 mm Value	40–47 45–47
Heat Distortion Temperature	ISO 75:Method A ISO 75:Method B	° C ° C	57.75 68.4
Coefficient of Linear Expansion	In-House	° C <sup>-1</sup>	0.498×10.6

### FIRE CLASSIFICATION

Test	Test Method	Units	Average Result
Fire Classification 3mm & 5mm	IEC 13501-1	Class	C-s3, d1

#### PROTECTIVE FILM

- PE film on one side as standard
- No branding over the film
- Digital marking of sizes over on long side

#### TOLERANCE FIXED FOR EACH THICKNESS

- -0 to + 2 mm on width
- -0 to + 10 mm on length
- Rectangularity is max 2 mm per meter

#### TOLERANCE IN THICKNESS

- +/- 0.15 mm for 1–2 mm thickness
- +/- 0.15 mm for 3–6 mm thickness
- +/- 0.30 mm for 8–10 mm thickness
- +/- 0.50 mm for 15–19 mm thickness

#### SPECIAL REQUIREMENTS ON REQUEST

- Additional thicknesses as required
- Non standard sheet dimensions are available

#### NOTE:

After printing the ink must be perfectly dry so as to avoid any effect on the later combination with the application surface. The surface on which material is applied must be free of dust, grease, lubricant and any other substances which may hinder the film from adhesion. Freshly lacquered or painted surfaces should be allowed to dry for no less than three weeks. The compatibility of particular lacquers and paints should be tested by the user, prior to application on the material.

All rights reserved. All trademarks and registered trademarks are the property of their respective owners. The information included in the present publication is based upon our knowledge as well as practical experience and can be changed without prior notice. This data is displayed only in order to serve as a source of information and is given without guarantee and does not constitute a warranty. Owing to wide range of possible uses and applications, customers should independently verify the appropriateness.