

To Order: StahlsID.com • 800.4.STAHLS • Fax: 800.346.2216 International: StahlsInternational.com • 586.772.5551

Canada: StahlsCanada.com • 800.521.5255

# Fashion-FILM™



MATERIALinto cutter so that the carrier is on the bottom.



PREHEAT &
POSITION—
Preheat garment for 10

seconds, prior to application. Position weeded design on garment with the carrier side up (reads left to right). Place cover sheet over graphic.

## Recommended Fabrics

Cottor

Polyester

Lycra®/ Spandex blends

Due to the combination of fabrics, weaves, coatings and dyes used in the textile industry, Stahls' recommends and provides samples of our materials and medias for testing.

### **Accessories Required**

Kraft Paper or Reusable Cover Sheet EZ Weeder® or Tweezers

## **Cutting Notes**

You should always test cut prior to any production run. For optimal cutting and weeding, maintain a line thickness of at least 1/16" for lettering & logos.

#### **Care Instructions**

Machine wash using mild detergent. Do not use bleach. Dry at a normal dryer setting on household machines. Do not dry clean.

## **Multi-Color Designs**

Apply background for 2 seconds; Peel HOT. Apply foreground at 320° F, medium pressure for 15 seconds; Peel HOT.

#### **Storage**

Stahls' Fashion-FILM™ should be stored around 65 to 70 degrees Fahrenheit with 50% relative humidity. We recommend shelf life for materials be one year.



**CUT LOGO,** words or numbers in reverse (mirror image).



HEAT APPLY— Temperature: 320°F; 160°C Time: 15 seconds Pressure: medium #5 on Hotronix®

Tip: A Heat Printing Pillow or Print Perfect Pad is recommended for even pressure when working around zippers, buttons, heavy seams or mesh reversible jerseys.



**WEED** away excess material leaving only the desired graphic on the carrier.



PEEL HOT-

## **CUTTER GUIDELINES**

CUTTER	BLADE	FORCE	OFFSET	SPEED
Roland GX-24	45°	80g-120g	.25	50cm/s
Ioline 100	45°	90g	.15	12:15
Ioline 300	30°	100g	.15	12:15

All technical information and recommendations are based on tests we believe to be reliable. However, we cannot guarantee performance for conditions not under manufacturer's control. Before using, please determine the suitability of product for its intended use. The user assumes all risk and liability whatsoever in connection with the use of this product. Seller's and manufacturer's only obligation shall be to replace such quantity of the product proved to be defective by manufacturer.

CAD-CUT, Fashion-FILM, & Hotronix are trademarks & ® trademarks of Stahls' ID Direct™ with one or more patents or patents pending.
© Stahls' ID Direct™ 2013 - All International Rights Reserved